

QUALITY CONTROL LABORATORY AND R&D

ACCELERATED WEATHERING TEST

<u>REPORT NUMBER</u> : RP_442
<u>DECORATION</u> : 93019-201
<u>BASE</u> : POWDER COATING V1
<u>TEST</u> : XENON TEST
<u>TOTAL DURATION</u> : 1000 HOURS



SAMPLE EVALUATION

RESIDUAL GLOSS	100%
COLOUR VARIATION ΔE	1.00
GREY SCALE	5
FINAL RESULT	PASS

QUALITY CONTROL LABORATORY AND R&D

ACCELERATED WEATHERING TEST

<u>REPORT NUMBER</u> : 478
<u>DECORATION</u> : S.OFF 93148-001
<u>BASE</u> : POWDER COATING V1
<u>TEST</u> : XENON TEST
<u>TOTAL DURATION</u> : 1000 HOURS



SAMPLE EVALUATION

RESIDUAL GLOSS	100%
COLOUR VARIATION ΔE	1.76
GREY SCALE	5
FINAL RESULT	PASS

QUALITY CONTROL LABORATORY AND R&D

ACCELERATED WEATHERING TEST

<u>REPORT NUMBER</u> : 476
<u>DECORATION</u> : S.OFF 93147-001
<u>BASE</u> : POWDER COATING V1
<u>TEST</u> : XENON TEST
<u>TOTAL DURATION</u> : 1000 HOURS




SAMPLE EVALUATION

RESIDUAL GLOSS	106%
COLOUR VARIATION ΔE	1.7
GREY SCALE	4/5
FINAL RESULT	PASS

QUALITY CONTROL LABORATORY AND R&D

ACCELERATED WEATHERING TEST

<u>REPORT NUMBER</u> : RP_443
<u>DECORATION</u> : 93021-201
<u>BASE</u> : POWDER COATING V1
<u>TEST</u> : XENON TEST
<u>TOTAL DURATION</u> : 1000 HOURS




SAMPLE EVALUATION

RESIDUAL GLOSS	100%
COLOUR VARIATION ΔE	0.75
GREY SCALE	5
FINAL RESULT	PASS

QUALITY CONTROL LABORATORY AND R&D

ACCELERATED WEATHERING TEST

<u>REPORT NUMBER</u> : RP_444
<u>DECORATION</u> : 93020-101
<u>BASE</u> : POWDER COATING V1
<u>TEST</u> : XENON TEST
<u>TOTAL DURATION</u> : 1000 HOURS



SAMPLE EVALUATION

RESIDUAL GLOSS	100%
COLOUR VARIATION ΔE	0.55
GREY SCALE	4/5
FINAL RESULT	PASS